

## TECHNICAL SPECIFICATION

**MODEL / REFERENCE** : CLASSIC NEW MARFIL (A62GZNMF - BE0.G0 C6 P)  
**NOMINAL SIZE** : 120 X 260 CM (RECTIFIED)  
**NOMINAL THICKNESS** : 6.0 MM  
**TYPE OF PRODUCT** : GRES PORCELLANATO TILE  
**NATURE OF SURFACE** : LAPPATO  
**GROUP** : Bla  
**REF. STANDARD** : INTERNATIONAL STANDARD ISO 13006:2018

TEST DESCRIPTION	STANDARD TEST METHOD	STANDARD REQUIREMENTS	RAK CERAMICS SPECIFICATION
Surface Quality	BS EN ISO 10545 - 2	A minimum of 95% of the tiles are to be free from visible defects	Minimum of 95% of the tiles are free from visible defects
Length & Width	BS EN ISO 10545 - 2	± 1.0 mm	± 1.0 mm
Thickness	BS EN ISO 10545 - 2	± 0.5 mm	± 0.3 mm
Straightness of Sides	BS EN ISO 10545 - 2	± 0.8 mm	± 0.8 mm
Rectangularity	BS EN ISO 10545 - 2	± 1.5 mm	± 1.2 mm
Surface Flatness: Center Curvature	BS EN ISO 10545 - 2	± 1.8 mm	± 1.8 mm
Surface Flatness: Edge Curvature	BS EN ISO 10545 - 2	± 1.8 mm	± 1.5 mm
Surface Flatness: Warpage	BS EN ISO 10545 - 2	± 1.8 mm	± 1.5 mm
Water Absorption	BS EN ISO 10545 - 3	≤ 0.5 %	≤ 0.4 %
Breaking Strength	BS EN ISO 10545 - 4	≥ 700 N	≥ 700 N
Modulus of Rupture	BS EN ISO 10545 - 4	≥ 35 N/mm <sup>2</sup>	≥ 35 N/mm <sup>2</sup>
Resistance to Surface Abrasion	BS EN ISO 10545 - 7	Report abrasion class	PEI Class 2 - 4
Coefficient of Linear Thermal Expansion	BS EN ISO 10545 - 8	Test method available	≤ 7 X 10 <sup>-6</sup> /°C
Resistance to Thermal Shock	BS EN ISO 10545 - 9	Test method available	No visible defect
Crazing Resistance	BS EN ISO 10545 - 11	Required	No crazing
Frost Resistance	BS EN ISO 10545 - 12	Required	No visible damage
Resistance to Household Chemicals & Swimming Pool Salts	BS EN ISO 10545 - 13	Minimum Class B	Class A No visible effect
Resistance to Low Concentrations Acids & Alkalis	BS EN ISO 10545 - 13	Manufacturer to state classification	Class LA No visible effect
Resistance to Staining	BS EN ISO 10545 - 14	Minimum Class 3	Min. Class 4 Stains removed

NOTE: This Technical Specification is applicable only to tiles in Choice "A".

Signed:  
For RAK Ceramics PJSC

  
RUEL PEREZ  
VP - QA/QC

Date of Issue: 30/06/2021



RAK Ceramics PJSC  
P.O. Box 4714  
Ras Al Khaimah  
United Arab Emirates

Tel. +971 7 246 7000  
Fax. +971 7 244 5270

RAKCERAMICS.COM